

DATA SHEET - GT 1067

GT 1067 was developed by combining a silver-plated copper filled conductive silicone (GT1000) with an environmental sealing fluorosilicone (GT47). This mixture aims to meet the constraints of a corrosive environment by dissociating the shielding function from the environmental sealing function.

- Good EMP resistance
- Both electrically and thermally conductive
- Excellent stability over time

Properties - Conductive part	Standards - Test	GT 1000
Elastomer binder		Silicone
Conductiver filler		Silver-plated copper
Volume resistivity Ω.cm	MIL G 83528	< 0.005
Hardness shore A	ASTM D 2240	82 ± 7
Density g/cm ³	ASTM D 792 method A	3.40
Break resistance Mpa	ASTM D 412 method A C	2.20
Elongation at break %	ASTM D 412 method A C	250
Tear strength kg/cm	ASTM D 624 C	13.70
Residual deformation after compression 70 hours at 100°C (%)	ASTM D 395 method B	17.50
Shielding performance : 20 MHz 100 MHz 500 MHz 2 GHz 10 GHz		130 dB 140 dB 120 dB 120 dB 120 dB
Working temperature °C		-55 to +125
Color		Beige

Properties - Sealing part	Standards- Test	GT 67
Specific mass at 25°C	ASTM D 792	1.46
Hardness Shore A ± 5	ASTM D 2240	60
Tensile strength Psi Mpa	ASTM D 412	1200 8.30
Elongation %	ASTM D 412	300
Residual deformation after compression 22 hours at 177°C (%)	ASTM D 395 method B	25
Color		Light blue

AVAILABLE FORMATS

Molded

Customized cut

Extruded

Vulcanization bonding

