

DATA SHEET - GT 2047

GT 2047 was developed by combining a pure silver filled conductive silicone (GT2000) with an environmental sealing fluorosilicone (GT47). This mixture aims to meet the constraints of a corrosive environment by dissociating the shielding function from the environmental sealing function.

- **Highly conductive**
- **Very low volume resistivity**
- **Excellent attenuation performance**
- **High-temperature resistance (peak 200°C)**

Properties - Conductive part	Standards - Test	GT 2000
Elastomer binder		Silicone
Conductive filler		Pure silver
Volume resistivity Ω.cm	MIL G 83528	< 0.006
Hardness shore A	ASTM D 2240	75 ± 7
Density g/cm ³	ASTM D 792 Method A	3.90
Break resistance Mpa	ASTM D 412 Method A C	4.61
Elongation at break %	ASTM D 412 Method A C	355
Tear strength kg/cm	ASTM D 624 C	14
Residual deformation after compression 70 hours at 100°C (%)	ASTM D 395 Method B	33.12
Shielding performance :		110 dB
20 MHz		110 dB
100 MHz		110 dB
500 MHz		110 dB
2 GHz		110 dB
10 GHz		110 dB
Working temperature °C		-55 to +125
Color		Light beige

Properties - Sealing part	Standards - Test	GT 47
Specific mass at 25°C	ASTM D 792	1.43
Hardness Shore A ± 5	ASTM D 2240	40
Tensile strength Psi Mpa	ASTM D 412	1250 8.60
Elongation %	ASTM D 412	400
Residual deformation after compression 22 hours at 177°C (%)	ASTM D 395 Method B	20
Color		Blue

AVAILABLE FORMATS

- Molded
- Customized cut
- Extruded
- Vulcanization bonding

