



GETELEC

We protect your electronics

DATA SHEET - GT 2060

GT 2060 was developed by combining a pure silvr filled conductive silicone (GT2020) with an environmental sealing silicone (GT60). This mixture aims to meet the constraints of a corrosive environment by dissociating the shielding function from the environmental sealing function.

- **Highly conductive**
- **Very low volume resistivity**
- **Excellent attenuation performance**
- **High temperature resistance (peak 200°C)**

Properties - Conductive part	Standards - Test	GT 2020
Elastomer binder		Silicone
Conductiver filler		Pure silver
Volume resistivity $\Omega \cdot \text{cm}$	MIL G 83528	< 0.006
Hardness shore A	ASTM D 2240	75 \pm 7
Density g/cm^3	ASTM D 792 Method A	3.90
Break resistance Mpa	ASTM D 412 Method A C	4.61
Elongation at break %	ASTM D 412 Method A C	355
Tear strength kg/cm	ASTM D 624 C	13.73
Residual deformation after compression 70 hours at 100°C (%)	ASTM D 395 Method B	33.12
Shielding performance :		
20 MHz		110 dB
100 MHz		110 dB
500 MHz		110 dB
2 GHz		110 dB
10 GHz		110 dB
Working temperature °C		-55 to +125
Color		Light beige

Properties - Sealing part	Standards - Test	GT 60
Specific mass at 25°C	ASTM D 792	1.27
Hardness Shore A \pm 5	ASTM D 2240	60
Tensile strength Psi Mpa	ASTM D 412	950 6.55
Elongation %	ASTM D 412	300
Residual deformation after compression 22 hours at 177°C (%)	ASTM D 395 method B	33
Color		Blue

AVAILABLE FORMATS

- Molded
- Customized cut
- Extruded
- Vulcanization bonding

